

APCOTHERM EPN 200 / APCOTHERM 200 CUI



PRODUCT DESCRIPTION

Two components high build epoxy phenolic novolac coating for high temperature service.

FEATURES & RECOMMENDED USE

- Designed to provide excellent corrosion & chemical resistance when used in high temperature service
- Recommended as a corrosion resistant barrier to protect for steelwork under thermal insulation subject to wet and dry cycles from -196°C to + 230°C
- Suitable for exposure to a wide range of corrosive environments and exterior of insulated or un-insulated steel pipeline, process equipment's, vessels, etc., operating continuously up to 230°C and intermittently at 250°C
- Self-priming; excellent adhesion on blast cleaned steel
- Excellent resistance to "Thermal Shock" experienced during rapid heating and cooling conditions

TECHNICAL DATA

Colour	Limited Shades
Gloss	Matt
Volume Solids	Approx. 80%
Recommended DFT / Coat	100 - 125 µm
Theoretical Coverage Capacity	8.0 sq.mtr/ ltr @ 100 µm DFT 6.4 sq.mtr/ ltr @ 125 µm DFT
Drying Time at 30°C	Surface Dry : 5 hours Hard Dry : 12 hours Full Cure : 7 days
Over coating interval 30°C	Min. : 12 hours Max. : 4 days

The physical values are subject to normal manufacturing tolerances, colour and testing variances.

The volume solids indicated are as per ASTM D 2697 air drying method.

The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc.

The information provided above is at 30° C and 65% relative humidity.

DIRECTION FOR USE

Surface Preparation

General

- Surfaces must be dry, clean and free from contaminants
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Oil and grease should be removed as per SSPC-SP1 solvent cleaning
- Surface should be checked and treated in accordance with ISO 8504 prior to priming

Blast Cleaning

- Steel, abrasive blast clean to min. Sa 2.5 as per Swedish specification. In case oxidation has occurred between blasting and application of Apcotherm EPN 200 / Apcotherm 200 CUI, the surface should be re-blasted
- A blasting profile of (Rz) 50-75 µm is recommended

Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C
- Relative humidity should be below 85%
- Good ventilation is required in confined areas to ensure proper curing

Mixing

- Apcotherm EPN 200 / Apcotherm 200 CUI is supplied in two packs. Stir the base and hardener separately. If settling is observed in the base or hardener, loosen the settled material with the help of hand stirrer followed by power driven stirrer (at lower RPM) for quick homogenous mixing
- Mix hardener gradually into the base under continuous stirring as per the mixing ratio. Once the unit has been mixed, it should be consumed within the working pot life. In case of part mixing (which should be avoided), close the lids of containers tightly to avoid contact with atmospheric moisture
- Thinner should be added after mixing the components and post the induction time. Addition of too much thinner will lead to reduced sag resistance

Mixing Ratio (by volume)	Base : Hardener 4 : 1
Induction Time	10 Minutes
Pot Life at 30°C	3 Hours

Application

Airless Spray	
Recommended thinner	T - 141
Volume of thinner	0 - 5%
Nozzle orifice	0.43 - 0.53 mm (17 – 21 Thou)
Nozzle pressure	17 – 20 MPa (= approx. 170 – 200 atm; 2500 – 2900 p.s.i.)
Cleaning Thinner	T 141
Brush / Roller	<i>(Suitable for stripe coating and small areas)</i>
Recommended thinner	T - 141
Volume of thinner	0 - 5%

**Note: Depending on recommended thickness & application condition*

Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipment's immediately after use with Thinner T 141. It is recommended to periodically flush out spray equipment during the course of the working day. The frequency of cleaning will depend on amount sprayed, temperature and time gap
- All surplus material and empty containers should be disposed of in accordance with appropriate regional legislation

Product Characteristics

- Maximum film build in one coat is best attained by airless spray. Air spray (pressure pot) may require a multiple cross spray pattern to achieve optimum film build. By brush application 50-75 µm is achieved in one coat and multiple coats will be required to achieve the total specified thickness
- Typical system of two coats at 100 µm is recommended for optimum performance. By brush application, a three coat system to give a total dry film thickness of 200 µm is recommended. The total system thickness must not exceed 300 µm in order to avoid cracking at high temperature service

- The maximum performance is achieved after complete curing
- As common with all epoxies Apcotherm EPN 200 / Apcotherm 200 CUI will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance. The actual rate of chalking will depend upon climatic conditions and will normally be limited to a thin surface layer
- Apcotherm EPN 200 / Apcotherm 200 CUI is not recommended for immersion services
- Premature exposure to ponding water will cause a colour change
- Application of stripe coat on welded/edges/crevice's area to be done prior full coat application

PACK SIZE	20 L (Base : 16 L & Hardener : 4 L)
STORAGE	Shelf Life: At least 12 months at 30°C for original unopened pack, subject to inspection thereafter Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash Point: Base - Not less than 24°C; Hardener - Not less than 24°C VOC: Approx. 190 ± 20 gm/ ltr (depending on shades) as per USA-EPA Method 24 Product Weight: Approx. 1.55 ± 0.05 kg/ ltr (depending on shades)

SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection is always recommended while spraying paint
- Please refer our Material Safety Data Sheet prior to using the product

Disclaimer: To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.

'APCOTHERM' is a Trademark of Asian Paints Ltd. | Licensed user: Asian Paints PPG Pvt. Limited.

Head Office: Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, Near Religare Building, S.V. Road, Goregaon (W), Mumbai 400 062
Tel No: 022 62182700, **CIN:** U24110MH2011PTC220557, **Email:** customercare.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com