

# HAWCOPLAST PP series

## Polyester coatings



The datasheet is standard for the range HAWCOPLAST PP series products and specific products within the range can vary. Datasheet for individual products are available.

### PRODUCT DESCRIPTION

HAWCOPLAST PP series products are thermosetting powder coatings based on Polyester resins which are available in smooth glossy, semi glossy, matt, structure, texture and metallic finishes in wide range of colours & shades and can be applied to ferrous and non-ferrous substrates.

HAWCOPLAST PP series products can be custom designed to meet customer specifications.

Suitable for outdoor applications.

### PRODUCT SPECIFICATION

Chemistry	Polyester
Physical Appearance	Free flow powder
Specific Gravity	1.4 - 1.7
Application DFT	60-80 micron for smooth, texture & metallic finishes 70-100 micron for structure finish
Curing Schedule	200°C object temp. for 10 min.

### FILM PERFORMANCE

	Product series Product code	PPG (6120)	PPS (6122)	PPS (6122)	PPS (6122)	PPS (6122)	PPM (6121)	PPT (6123)	PPTF (6135)	PPC
Test description	Test method	Specification								
Finish	Visual	Smooth	Smooth	Smooth	Smooth	Smooth	Smooth	Structure	Texture	Metallic
Gloss at 60° head	ASTM D 523	>90	75-85	65-75	40-60	20-30	<20	20-30	5-10	--
Impact resistance	ASTM D 2794	100 KG.CM	100 KG.CM	100 KG.CM	80 KG.CM	80 KG.CM	40 KG.CM	40 KG.CM	80 KG.CM	80 KG.CM
Scratch hardness	ASTM D 2197	2 KG								
Pencil Hardness	ASTM D 3363	2 H								
Adhesion	ASTM D 3359	GT-0 (100% adhesion)								
Cylindrical Mandrel	ASTM D 522B	5 mm								
Erichsen Cupping	DIN 53156	5 mm								
Salt Spray Resistance	ASTM B 117	500 Hrs.								
Humidity Resistance	ASTM D 2247	500 Hrs.								

**Test conditions:** All tests are carried under laboratory conditions on 0.8mm standard Tri-cationic Phosphated CRCA test panels with coating weight of 2-3 gm/sq.mt followed by powder coating at DFT 60-70μ for smooth & texture finish and at DFT 70-100μ for structure finish and cured at 200°C object temp. for 10 min.

## APPLICATION RECOMMENDATION

Pre-treatment	All substrates are to be cleaned & should be free from grease, oil & dust A suitable chromate conversion coating is recommended for Aluminum substrate. Passivated Zinc phosphate coating is recommended for steel substrate. for better results Sand Blasting / Grit blasting to at least SA 2.5 followed by passivated tri-cationic phosphating process with coating weight of 2-3 gm/sq.mt is recommended
Application voltage	60 – 90 KV
Earthing	Proper & good
Compress air	Free from moisture, oil, dust & other impurities through flat jet spray nozzle
Thorough cleaning of the application & recovery system required between each change in powder to avoid contaminations & defects	

## SHELF LIFE AND STORAGE

Shelf life of six months from the date of manufacturing, if stored in closed store in dry & cool atmosphere below 30°C & 60% RH throughout the period.

The cartons should be stacked 1+4 high. Avoid exposure to direct sunlight, heat and high humidity. Partly used material must be tightly closed after each removal and stored carefully inside the carton to avoid contamination & absorption of moisture.

## SAFETY INFORMATION

Please refer Material Safety Data Sheet prior to using the product

*The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current regulations. Use of the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from Asian Paints PPG Pvt. Ltd. as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the MSDS and the Technical Data Sheet for this product. We do not control the quality or the condition of the substrate or the many factors affecting the use and application of the product.*

*Unless agreed in writing, Asian Paints PPG Pvt. Ltd. do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. The information contained in this data sheet is subject to modification from time to time in the light of experience and continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.*

*APCOSHIELD and HAWCOPLAST are trademarks of Asian Paints Ltd. or licensed to Asian Paints PPG Pvt Ltd.*

Corp. Office: Plot No. 5, Gaiwadi Industrial Estate, S. V. Road, Goregaon (W), Mumbai 400062. Phone: +91-22-6218 2700

Regd. Office: 6A, Shantinagar, Santacruz (E), Mumbai 400055. Phone: +91-22-6218 1000

e-mail: [customercare.apppg@asianpaintsppg.com](mailto:customercare.apppg@asianpaintsppg.com). Customer Care no: +91-22-6218 2649

Website: [www.asianpaintsppg.com](http://www.asianpaintsppg.com) CIN: U24110MH2011PTC220557

